

# X-FLOW XF75 ULTRAFILTRATION MEMBRANE

## MEMBRANE ELEMENT DATASHEET

ARTICLE CODE : 2172DC195A

### GENERAL INFORMATION

XF75 is an ultrafiltration, used for the production of process and potable water from surface water, for wastewater polishing and reuse, in the pre-treatment of large SWRO plants, and in large-scale drinking water production. The XF75 module can be utilized in Pentair's unique solutions Aquaflex and X-Line.

### GENERAL SOLVENT RESISTANCE

Since the resistance of the membrane to solvents strongly depends on the actual process conditions, the indications given below should only be considered as guideline.

Acids	++
Bases	++
Organic esters, ketones, ethers	-
Aliphatic alcohols	+
Aliphatic hydrocarbons	+
Halogenated hydrocarbons	-
Aromatic hydrocarbons	-
Polar organic solvents	-
Oils	++

### MEMBRANE CHARACTERISTICS

- Hydrophilic membrane composed of a blend of polyvinylpyrrolidone and polyethersulfone
- A nominal pore size of 20 nm
- Structure asymmetric/microporous
- High performance and a very good anti-fouling behaviour
- Typical permeate quality SDI<3, turbidity <0,1 NTU
- Membrane filtration provides 99.9999% (LOG6) reduction of bacteria (*Pseudomonas diminuta*) and 99.99% (LOG 4) reduction of virus (MS2 colifages) by mechanical means. EPA Est. No. 090374-NLD-001

### CLEANING CHEMICAL RESISTANCE

#### Sodium Hypochlorite

- Typical 200 ppm, at  $\leq 40\text{ }^{\circ}\text{C}$  at  $\geq \text{pH } 10$
- Maximum 500 ppm
- 250.000 ppm hours cumulative;  $\geq \text{pH } 10$

#### Chlorine Dioxide

- Typical 1 ppm, at  $\leq 40\text{ }^{\circ}\text{C}$
- Maximum 2 ppm
- 90.000 ppm hours cumulative;  $\text{pH } 11$

#### Hydrogen Peroxide

- Typical 200 ppm, at  $\leq 40\text{ }^{\circ}\text{C}$
- Maximum 500 ppm
- 350.000 ppm hours cumulative

Note:

The above figures for oxidant contact represent the membrane resistance to each individual oxidizing agent. The total combined exposure for Sodium Hypochlorite and Chlorine Dioxide will be calculated as follows:

$$\text{Combined exposure (NaOCl + ClO}_2\text{)} = 2.6 \times \text{Exposure to ClO}_2\text{ (in ppm hours)} + \text{Exposure to NaOCl (in ppm hours)} < 250.000 \text{ ppm hours}$$

As a good working practice and in order to maximise the lifetime of the membrane it is advised to reduce the membrane exposure to oxidising agents to a minimum. Exposure limits are also affected by temperature, pH and the presence of metals. In order not to exceed maximum exposure limits, membranes must be preserved free of any oxidising agent when the plant is stopped.

#### Acids

Hydrochloric Acid	++
Nitric Acid	++
Sulphuric Acid	++
Phosphoric Acid	++
Acetic Acid	++
Citric Acid	++


pH > 2 during filtration  
pH > 1 during cleaning

#### Bases

Sodium Hydroxide (<4%)	++
Potassium Hydroxide (<4%)	++

pH < 12 during filtration  
pH < 13 during cleaning

Membrane diameter mm [mil]	Effective membrane area $\text{m}^2$ [ $\text{ft}^2$ ]	Feed connection DO mm [Inch]	Module length $L_0$ mm [Inch]	Permeate connection $d_0$ mm [Inch]
0.72 [28.3]	75 [807]	220.0 [8.66]	1537.5 [60.52]	51.6 [2.03]



# X-FLOW XF75 ULTRAFILTRATION MEMBRANE

## MEMBRANE ELEMENT DATASHEET

### OPERATING SPECIFICATIONS

Max. trans-membrane pressure Filtration	Max. trans-membrane pressure Backwash	Temp. range
kPa [psi]	kPa [psi]	°C [°F]
100 [14.5]	200 [29]	0-40 [32-104]

- Backwash water should be free of particulates and should be of UF permeate quality or better
- Backwash pumps should preferably be made of non-corroding materials, e.g., plastic or stainless steel. If compressed air is used to pressurize the backwash water, do not allow a two-phase air/water mixture to enter the element
- To avoid mechanical damage, do not subject the membrane module or

element to sudden temperature changes, particularly decreasing. Bring the module or element back to ambient operating temperature slowly (max. value 3 °C/min). Failure to adhere to this guideline can result in irreparable damage

Operation of membrane modules at any combination of maximum limits of pH, concentration, pressure or temperature, during cleaning or production, will influence the membrane lifetime.

### TECHNICAL SPECIFICATIONS

#### Weight Specifications

Dry weight of membrane element  
ca. 34 kg [75 lbs]

Membrane element filled with water  
ca. 66 kg [145 lbs]

#### Materials of Construction

Housing	PVC white
Flow distributor	PVC
Potting	PU resin
Membrane	PES/PVP

#### Process Characteristics (Water, 20 °C)

Hydraulic membrane diameter	Crossflow flow rate (*)	Pressure-drop across module at 0.2 m/s	Pressure-drop across module at 0.5 m/s
mm [mil]	m <sup>3</sup> /h [gpm]	kPa [psi]	kPa [psi]
0.72 [28.3]	49.9 x v [219.7 x v]	19 [2.8]	47.7 [6.9]

(\*) superficial velocity (v) in m/s [ft/s]

### STORAGE

New membrane modules can be stored as supplied in the original packaging. The membrane modules contain an aqueous preservation solution of glycerine (20wt%) and sodium metabisulfite (1wt%) to prevent dehydration and control bacterial growth. The membrane modules are packed in plastic bags which are vacuum sealed to keep the moisture in the module. Membrane modules should be stored in a dry, normally ventilated place, away from sources of heat ignition and direct sunlight.

Storage temperature should be between 0 and 40 °C. Pentair instructions for transport and storage are to be followed at all times and available upon request. It is recommended to have the membrane modules installed into the UF skids and commissioned as soon as possible. The membrane shelf life is maximum 6 months from the date the modules are announced ready for delivery ex works Pentair warehouse. After expiry of the shelf life all warranties are null and void.



**Headquarter:** 54/18 Bui Quang La, Ward 12, Go Vap District, HCMC, Vietnam  
**Office:** 77 DHT10B, Dong Hung Thuan Ward, District 12, HCMC, Vietnam  
**Phone:** (028) 6258 5368 - (028) 6291 9568  
**Email:** info@atswatertechnology.com  
**Website:** www.atswatertechnology.com



**ATS WATER  
TECHNOLOGY**

#### X-FLOW BV

P.O. BOX 739, 7500 AS ENSCHEDE, NETHERLANDS WWW.XFLOW.PENTAIR.COM

Note: The information and data contained in this document are based on our general experience and are believed to be correct. They are given in good faith and are intended to provide a guideline for the selection and use of our products. Since the conditions under which our products may be used are beyond our control, this information does not imply any guarantee of final product performance and we cannot accept any liability with respect to the use of our products. The quality of our products is guaranteed under our conditions of sale. Existing intellectual property rights must be observed.

XF75\_DS\_ENG\_V2620 © 2020 Pentair. All Rights Reserved.